

French Limestone

French Limestone is a soft limestone-look surface in the Ivory colourway, made from cement blended with mineral fragments to create gentle variation and a natural, tactile feel. Designed for internal floors and walls, the range allows a consistent look to flow throughout the home while introducing texture where needed.

The collection is available in a matt finish across 600x1200mm, 300x1200mm, 200x1200mm, 600x600mm, 300x600mm, 300x300mm, French Pattern, 300x330mm Brickbond Mosaic, and 200x200mm Tumbled Fingers, supporting both open spaces and detailed areas.

For applications requiring additional surface character, textured options including 600x600mm and French Pattern offer a more tactile finish, ideal for wet areas, entry zones and feature flooring.

French Limestone, Ivory provides a refined, easy-to-spec limestone aesthetic with the flexibility to move seamlessly from large-format layouts to intricate design features within the same material family.



FRENCH LIMESTONE



26 Daisy Street
Revesby NSW 2212
P 02 9772 2088
E sales@japanceramics.com.au
japanceramics.com.au

COLOURS, FORMATS & FINISHES



Ivory

Matt | P3

600 x 1200mm	●
300 x 1200mm	●
200 x 1200mm	●
600 x 600mm	●
300 x 600mm	●
300 x 300mm	●
300 x 330mm Brickbond Mosaic	●
200 x 200mm Tumbled Fingers	●
French Pattern	●

Textured | P5

French Pattern	●
600 x 600mm	●



FINISH: **TEXTURED** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V3
FINISH: **MATT** | CATEGORY: PORCELAIN TILES | EDGE DETAIL: RECTIFIED | V RATING: V3





Brickbond Mosaic
FLMIVBB (matt)




300 x 600mm
FLMIV36 (matt)




600 x 1200mm
FLMIV612 (matt)



Fingers Mosaic
FLMIVTF (matt)



300 x 300mm
FLMIV30 (matt)




300 x 1200mm
FLMIV312 (matt)



200 x 1200mm
FLMIV212 (matt)



600 x 600mm
FLMIV60 (matt)
FLMIV60E (textured)
FLMIV60-20 (textured 2CM)



398 x 600mm Coping
FLMIV46-20L (textured 2CM)



French Pattern
FLMIVFR (matt)
FLMIVFRE (textured)

Technical Specifications

Properties	Test Method	Required Value	Value	Applies to
 Water absorption	EN ISO 10545-3	$\leq 0.5\%$	$\leq 0.5\%$	Full range
 Determination of dimensions	EN ISO 10545-2	Length and width $\pm 0.6\%$ Thickness $\pm 5.00\%$ Transmutation $\pm 0.5\%$	Length and width $\pm 0.2\%$ Thickness $\pm 2.1\%$ Transmutation $\pm 0.2\%$	Full range
 Breaking strength	EN ISO 10545-4	≥ 1300 N	≥ 2208 N	Full range
 Modulus of rupture	EN ISO 10545-4	≥ 35 N/mm ²	≥ 47 N/mm ²	Full range
 Abrasion resistance	EN ISO 10545-4	Class 3 min	Class 3	Full range
 Slip resistance (wet pendulum test)	AS 4586-2013/ AMDT1-2017	N/A	P3 - Matt P5 - Textured	Matt Textured
 Chemical resistance	EN ISO 10545-13	Min. GB	Class GA	Full range
 Stain resistance	ISO 10545-14	Min class 3	Class 5	Full range
 Origin	N/A	N/A	China	Full range
 Shade variation	N/A	N/A	V3	Full range



Packing Information

Tile Description		Quantity per Box	Quantity per m2		Quantity per Pallet	
Size (mm)	Finish	Pieces	Pieces	Weight	m2	Boxes
Brickbond Mosaic	Matt	11	11.00	2.16kg	N/A	N/A
Fingers Mosaic	Matt	11	11.00	0.83kg	N/A	N/A
300 x 300	Matt	11	11.11	22.00kg	55.44	56
300 x 600	Matt	8	5.56	22.00kg	57.60	40
600 x 600	Matt Textured	4	2.78	22.00kg	57.60	40
200 x 1200	Matt	5	4.17	23.00kg	68.80	54
300 x 1200	Matt	4	2.78	23.00kg	57.60	40
600 x 1200	Matt	2	1.39	23.00kg	40.32	28
French Pattern	Matt Textured	6	8.33	23.60kg	31.68	44



The data and information contained in these specification sheets are indicative only unless stated otherwise. As Japan Ceramics cannot control the conditions under which these products are manufactured, the specifications supplied should be considered as suggested guidelines only and are subject to batch variation. The information contained in these specification sheets should not be considered a warranty, expressed or implied, including, but not limited to, a warranty of merchantability or fitness for a particular purpose. To the maximum extent permitted by law, ColorTile will not be responsible for damages of any nature resulting from the use or reliance upon the information contained in this data sheet. No express or implied warranties are given in respect of any specification provided herein other than those that cannot be excluded under the Australian Consumer Law.

Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.

Slip Check to AS 4586-2013 French Limestone

Report Number: R35408

Report Date: 1 April 2026

Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

Issued by

Safe Environments Pty Limited
6/7 Inglewood Place
Norwest NSW 2153

Prepared for

Japan Ceramics Pty Ltd
26 Daisy Street
Revesby NSW 2212

Approved by



Brooke Wright
Authorised Signatory

1 April 2026

Test Report No. R35408

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by: Japan Ceramics Pty Ltd
Client Address: 26 Daisy Street
Revesby NSW 2212
Product Manufacturer: FOSHAN PELERINA CERAMICS CO. LTD
Product Description: French Limestone

Test conducted according to: AS 4586:2013 Appendix A
Sampling Procedures: Performed by client and tested as received.
Location: 6/7 Inglewood Place, Norwest NSW 2153

Conducted by: Harrison Toth

Date: 1 April 2026
Sample: Unfixed
Rubber slider used: Slider 96
Slope of specimen: Tested on a flat level surface
Direction of Test: N/A

Temperature: 25°C
Cleaning: None
Conditioned: Grade P 400 paper dry followed by wet lapping film

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	45	40	39	46	40

Reported SRV of Sample:	42
Class:	P3

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.

Slip ratings are indicative only. Actual performance may vary depending on installation, surface conditions, and maintenance.

Slip Check to AS 4586-2013 French Limestone External

Report Number: R35511c

Report Date: 1 May 2026

Total Number of Pages 2

Safe Environments quality management system is certified to ISO 9001:2015

Accredited for compliance with ISO/IEC 17025 – Testing

NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration, inspection, proficiency testing scheme providers and reference materials producers reports and certificates

Issued by

Safe Environments Pty Limited
6/7 Inglewood Place
Norwest NSW 2153

Prepared for

Japan Ceramics Pty Ltd
26 Daisy Street
Revesby NSW 2212

Approved by



Carl Strautins
Authorised Signatory

1 May 2026

Test Report No. R35511c

Slip Resistance Classification of New Pedestrian Surface Materials

AS 4586-2013 Appendix A (Wet Pendulum Test)

The slip resistance classification has been determined for unused surfaces under specific conditions. Factors such as usage, cleaning systems, applied coatings and patterns of wear may affect the characteristics of the surface after classification. Standards Australia Handbook 198:2014 *Guide to the specification and testing of slip resistance of pedestrian surfaces* provides guidance for the selection of slip resistant pedestrian surfaces classified in accordance with AS 4586-2013. It is recommended that this test report be read in conjunction with AS 4586, HB 197 & HB 198.

Requested by: Japan Ceramics Pty Ltd
Client Address: 26 Daisy Street
Revesby NSW 2212
Product Manufacturer: Foshan Pelerina Ceramics Co. Ltd
Product Description: French Limestone External

Test conducted according to: AS 4586:2013 Appendix A
Sampling Procedures: Performed by client and tested as received.
Location: 6/7 Inglewood Place, Norwest NSW 2153

Conducted by: Nathan Vanderburg

Date:	30 April 2026	Temperature:	22°C
Sample:	Unfixed	Cleaning:	None
Rubber slider used:	Slider 96	Conditioned:	Grade P 400 paper dry followed by wet lapping film
Slope of specimen:	Tested on a flat level surface		
Direction of Test:	N/A		

	Specimen 1	Specimen 2	Specimen 3	Specimen 4	Specimen 5
Mean BPN of last 3 swings:	60	60	57	59	59

Reported SRV of Sample:	59
Class:	P5

The expanded uncertainty (U_{95}) at the 95% level of confidence with a coverage factor (k) of 2 has been estimated to be 3 BPN or 8 %, whichever is the greater; sampling uncertainty has not been included. The expanded uncertainty should be considered when interpreting results or assessing conformity. Results relate only to items tested.